## Fireproof polystyrene foam, used for insulation e.g. in buildings, cars or furniture, comprises a mixture of styrene polymer, phenolic resin and expandable graphite

Publication number: DE19910257 (A1)		ar the
Publication date:	2000-09-21	Cited documents:
Inventor(s):	MARZOUKI TAIEB [DE]	<b>E</b> DE1090853 (B)
Applicant(s):	SCHWENK DAEMMTECHNIK GMBH & CO [DE]	🖹 US5721281 (A)
Classification:		🖹 US5719199 (A)
- international:	B29C44/44; C08J9/00; C08L25/06; C08L61/06; B29C44/34; C08J9/00; C08L25/00; C08L61/00; (IPC1-7): C08J9/00; B29C44/44; C08J9/14; C08K3/04; C08L25/06; C08L61/06	🖹 US5650448 (A)
- European:	B29C44/44; C08J9/00L25; C08J9/00L61; C08J9/00M; C08L25/06; C08L61/06	
Application number:	DE19991010257 19990308	

## Abstract of **DE 19910257 (A1)**

Priority number(s): DE19991010257 19990308

Fire-resistant polystyrene-based foam comprises a mixture of (A) 90-10 wt% styrene polymer (PS) and (B) 10-90 wt% phenolic resin, with the addition of (C) 5-50 wt% expandable graphite (based on mixture A + B). Independent claims are also included for (a) a process for the production of PS particle mouldings by making a mixture of phenolic resin, hardener and blowing agent and/or other conventional additives, mixing this with unexpanded PS beads, mixing the phenolic resin-coated or wetted beads with expandable graphite (C), introducing the mixture into a mould and sintering by the standard steam shock method; (b) an alternative process involving mixing PS beads with (C), combining the coated beads with the resin/hardener/blowing agent mixture, curing the phenolic resin in a mould and sintering as in (a).

Data supplied from the esp@cenet database — Worldwide